

Project: Density of RG 2400 products

Work request : Mech 19-4

Date started: 8/15/19

Testing concluded: 8/15/19

Scope: Determine density on our RG 2400 series products.

Procedure:

- Ensure samples are at 77 degrees F and test in accordance with ASTM D1475 Standard Test Method for Density of Liquid Coatings, Inks and Related Products.

Material tested:

- **RG 2400[®] LT- lot # 052819-**
- **RG 2400[®] AK- lot # lab batch**
- **RG 2400[®] CHW- lot # lab batch**
- **RG 2400[®] NP- lot # lab batch**
- **RG 2400[®] ET- lot # lab batch**

Results:

Product	Density	Specific Gravity
RG 2400[®] LT	8.5 lbs/gal	1.02
RG 2400[®] AK	7.74 lbs/gal	0.929
RG 2400[®] CHW	9.07 lbs/gal	1.09
RG 2400[®] NP	8.32 lbs/gal	0.998
RG 2400[®] ET	8.36 lbs/gal	1.00