



polyguard

MECHANICAL



Alumaguard® All Weather PRODUCT OVERVIEW

Alumaguard® All Weather weather-proofing cladding from Polyguard Products is the only flexible insulation cladding available in the market which combines the self-healing characteristics of rubberized asphalt with the ease of application and cold weather performance of acrylic adhesive-based products.

Alumaguard All Weather is a composite membrane consisting of a multi-ply embossed UV-resistant aluminum foil/polymer laminate to which is applied a layer of rubberized asphalt specially formulated for use on insulated duct and piping applications. A metalized polyester film coated with a high quality low temperature acrylic adhesive is then applied to the rubberized asphalt. A heavy duty release liner gives it its peel and stick functionality. It is designed to be used outdoors to weather-proof exterior insulated ductwork, piping or other insulated tanks, vessels and equipment. It resists moisture, air and vapor intrusion.

Alumaguard(or Alumaguard All-Weather) is not for use indoors or in return air plenum applications. In these applications Alumaguard Lite is recommended.

- Zero Perm (0.00 permeability)
- 10-Year Warranty
- Self-healing, puncture resistant
- Aluminum facing is UV stable
- Acrylic adhesive allows installation down to 10°F
- No pinning or activator required
- Excellent emissivity
- Can be used year round

Alumaguard Technical Properties and Testing

Membrane Property	Test Method	Results
Product Thickness (without liner)	Micrometer	54 mils 57 mils (Cool Wrap)
Product Weight	Scale	0.3 lbs/sf
Water Vapor Transmission (grains/hr-ft ²)	ASTM E96-00	0.00
Permeance (US Perms)	ASTM E96-00	0.00
Peel Adhesion (to primed steel)	ASTM D1000	>12 lbs/in
Low Temperature Pliability	ASTM D146	No Cracks@-15°F
Tensile Strength (film only)	ASTM D882	35 lbs/in (MD) 45 lbs/in (XD)
Elongation (film only)	ASTM D882	18% (MD) 40%
Puncture Resistance (film only)	ASTM D1000	15 Lbf
Mold Resistance	ASTM C1338	Pass
Upper Temperature Limit	LAB	160°F
Emissivity	ASTM C1371	.030
Fire Performance	ASTM E84	FSI=0 SDI=0 Classification: A
Alumaguard Cool Wrap Properties and Test Results		Solar Reflectance Thermal Emittance
Cool Roof Rating Council(CRRC) Initial	0.86	0.82
Cool Roof Rating Council(CRRC) 3 Year	0.77	0.86
Energy Star 3 Year	0.84	0.78
California Title 24	Exceeds 0.75	Exceeds 0.75

REV060424