



- ① WALL SURFACE PREPARATION: PROVIDE CLEAN, DRY, FROST-FREE, RAW SUBSTRATES PRIOR TO POLYGUARD TRM FLASHING INSTALLATION
- ② WALL SURFACE DETAILING: POLYGUARD DETAIL SEALANT PW OR TRM SEALANT APPLIED AND TOOLED TO MINIMUM 3/4" CANT / FILLET OVER AND ALONG JOINT
- ③ WALL SURFACE PRIMING: POLYGUARD 650 LT LIQUID ADHESIVE OR CALIFORNIA SEALANT APPLIED AT A RATE OF 250 - 300 SF / GAL, OR 650 WB LIQUID ADHESIVE APPLIED AT A RATE OF 350 - 400 SF / GAL
- ④ WALL CORNER BOOTS: POLYGUARD PREFORMED OR FIELD-MADE INSIDE / OUTSIDE CORNER BOOTS OVER POLYGUARD 650 LT LIQUID ADHESIVE OR CALIFORNIA SEALANT APPLIED AT A RATE OF 250 - 300 SF / GAL, OR 650 WB LIQUID ADHESIVE APPLIED AT A RATE OF 350 - 400 SF / GAL
- ⑤ WALL CORNER FLASHING: POLYGUARD TRM FLASHING APPLIED AND CENTERED (6" ON EACH CONCRETE FACE) OVER CLEAN, DRY, FROST-FREE, RAW INSIDE AND OUTSIDE VERTICAL WALL CORNERS PREPARED WITH POLYGUARD 650 LT LIQUID ADHESIVE OR CALIFORNIA SEALANT APPLIED AT A RATE OF 250 - 300 SF / GAL, OR OVER 650 WB LIQUID ADHESIVE APPLIED AT A RATE OF 350 - 400 SF / GAL
- ⑥ WALL FLASHING: POLYGUARD TRM FLASHING APPLIED AND CENTERED (6" ON EACH FACE) OVER CLEAN, DRY, FROST-FREE, RAW SILL PREPARED WITH POLYGUARD 650 LT LIQUID ADHESIVE OR CALIFORNIA SEALANT APPLIED AT A RATE OF 250 - 300 SF / GAL, OR OVER 650 WB LIQUID ADHESIVE APPLIED AT A RATE OF 350 - 400 SF / GAL
- ⑦ WALL FLASHING EDGE SEAL: POLYGUARD DETAIL SEALANT PW OR TRM SEALANT APPLIED AND TOOLED TO MINIMUM 90 MILS OVER AND ALONG ALL TRM FLASHING SEAMS AND EXPOSED TERMINAL EDGES AS EDGE SEAL

FT3

ISOMETRIC @ TRM FLASHING - INSTALLATION SEQUENCE