



650 WRM

PRODUCT OVERVIEW

650 WRM is a strong, pliable, 60-mil, post-concrete pour self-adhesive waterproofing membrane/vapor retarder that virtually eliminates water and vapor transmission through concrete walls & slabs. 650 WRM is designed for use on foundation walls, mud slabs, sills and spandrel beams, tunnels, plaza decks, parking garages, and related applications where waterproofing is critical. It may also be used on wood or concrete block structures and insulated concrete forms (ICF). 650 WRM is available in 48"x 50' rolls.

- Winter installation in ambient and substrate surface temperatures of 10°F (-12°C) and rising.
- Strong, self-adhering sheet membrane with a thick, high strength, tough co-extruded backing.
- Outstanding Puncture Resistance: 2 times higher than the new AC 527 requirement when installed with our Polyflow®
- Superior Joints: Strong laps seams create a long lasting, water tight system - Outperforms the new AC 527
- Jobsite Adaptability: Flexible material that adapts to job site irregularities for ease of installation
- VERTICAL – designed for application to the exterior sides of vertical concrete foundation walls, tunnels, and related applications where waterproofing is critical.
- Can be utilized in the Dual Core System that capitalizes on both the advantages of a fluid-applied and sheet-applied membrane in a single system.

Property	Test Method	Typical Value
Film Color		Blue/White
Membrane Thickness	ASTM D 1000	60 mils
Tensile Strength – Membrane	ASTM D 412 Modified Die C	MD 546.4 PSI - TD 516.6 PSI
Elongation – Ultimate Failure of Rubberized Asphalt	ASTM D 412	MD 119.2% - TD 129.6%
Elongation – Ultimate Failure of Rubberized Asphalt	ASTM D 882 Modified	MD 241.3% - TD 286.3%"
Tensile Strength – Film	ASTM D 882	7294 PSI
Permeance	ASTM E 96 Method B	0.022 Perms
Peel Adhesion to Concrete	ASTM D 903	14.8 lbs./in. width
Peel Adhesion (Laps – Membrane to Membrane)	ASTM D 903	19 lbs./in. width
Lap Peel Adhesion	ASTM D 1876	17 lbs./in. width
Low Temperature Flexibility (-20°F)	ASTM D 1970 Modified	Pass
Pliability	ASTM D 146 180° bend over 1" mandrel at -25° F (-32°C)	No effect
Puncture Resistance – Membrane	ASTM E 154	56.2 lbs.
Resistance to Hydrostatic Head (minimum)	ASTM D 5385	231 ft.
Exposure to Soil Fungi	GSA-PBS 07115 (16 weeks)	No effect
Water Absorption (maximum)	ASTM D 570	0.1%

REV020326



Detail Tape
WRM



650 LT
Liquid Adhesive



California
Sealant



Detail
Sealant PW™



LM-85 SSL



LM-95



Polyflow®
15/15P



Polyflow®
18



Polyflow®
BD



Totalflow™



Totalflow™
End Outlet

Totalflow™
Tee Outlet