



Stretch Flex - Above Grade

PRODUCT OVERVIEW

Our signature product with years of infield service under its belt. Stretch Flex can be sprayed down to -20°F allowing design flexibility and cost savings of not having to tent a building in cold temperatures. You will be spraying when others are not.

This product is not available in the following states: Maryland, Delaware, Rhode Island, Connecticut, and California.

- Non-Permeable (0.216 perms)
- Solvent-Based
- Application Temperature range -20°F to 120°F.
- 6 Month UV resistance.
- 40 mil wet / 20 dry mils (40 sf/gal theoretical coverage rate)

Property	Test Method	Typical Value
Color		Gray
Service Temperature Range		-25°F to 185°F
Air Leakage & Durability	ASTM E 2357	0.0008 cfm/ft ²
Air Permeance - Gypsum Sheathing	ASTM E 2178	0.0017 cfm/ft ²
Air Permeance - Block	ASTM E 2178	0.00012 cfm/ft ²
Permeance to Water Vapor Transmission	ASTM E 96 Method A	0.058 Perms
Permeance to Water Vapor Transmission	ASTM E 96 Method B	0.216 Perms
Adhesion	ASTM D 4541	> 135 PSI Average
Resistance to Hydrostatic Head	ASTM D 5385	231 ft.
Tensile Strength	ASTM D 412 Modified Die C	387 PSI
Elongation	ASTM D 412 Modified Die C	515%
Nail Sealability	ASTM D 1970	Pass
Crack Bridging	ICC ES-AC 212	Pass
Surface Burning Characteristics of Building Materials	ASTM E 84-94; NFPA 255; ANSI 2.5; UL 723 Omega 1995	10 - Flame Spread Index 35 - Smoke Development
Evaluation of Fire Propagation Characteristics	NFPA 285	Compliant*
Category 1 40 C.F.R.§59.401 "Waterproofing Sealers and Treatments"		525 g/l VOC

*Related to specific assemblies

Companion Products



**Airlok®
200 BU/NP**

Flashing Sizes

6" x 100'
9" x 100'
12" x 100'
18" x 100'
24" x 100'



**Airlok®
UV 200 BU/NP**

Flashing Sizes

6" x 100'
9" x 100'
12" x 100'



**Airlok®
400 NP**

Flashing Sizes

6" x 75'
9" x 75'
12" x 75'
18" x 75'
24" x 75'



**Airlok®
UV Ultra 400 NP**

Flashing Sizes

6" x 75'
9" x 75'
12" x 75'



**Detail
Sealant PW™**

REV071024