


# RD-6®

## Product Overview



Polyguard RD-6® Coating System is a non-shielding anti-corrosion system used on buried and submerged line pipe, rehabilitation and new construction girth welds. RD-6 can also be used above ground but the coating must be protected from harmful UV rays by using RD-6 UV Overcoat. It consists of a liquid adhesive, a geotextile backed protective pipeline coating and SP-6 outerwrap. RD-6 is compatible for pipelines operating up to 145°F (63°C); for pipes operating above 145°F, RD-6 HT must be used.

Corrosion protection results from the polymer modified coating layer. Bonded to the outside surface of this coating is a strong, tightly woven, polypropylene geotextile fabric, which provides non-shielding properties plus high breaking strength and low elongation. RD-6 coating is manufactured in rolls for ease of application using a Polyguard approved machine such as the Wrapster or power operated machine. RD-6 is produced with a silicone coated release liner to prevent the layers from adhering to one another and assist in the application process.



**Non-shielding coating**



**Fast & efficient no cure application**



**Resistant to soil stress**



**Resists disbondment from pipe even if surface is less than perfect**



**Allows for immediate backfill**



**Factory controlled thickness**

PROPERTY	ASTM METHOD	TYPICAL RESULTS (Metric)	TYPICAL RESULTS (English)
Total Thickness - Single layer of RD-6 Coating	D 1000	1.27 mm	0.05 inches (50 mils)
Breaking Strength	D 1000	193 N/10mm width	110 Lbs.F/in. width
Elongation % at break	D 1000	< 30%	< 30%
Water Vapor Transmission Rate	E 96 Procedure B	.006 g/h•m <sup>2</sup>	.009 grains/h•ft <sup>2</sup>
Cathodic Disbondment 77°F (25°C), 30 days, 1.5V	G 8	< 5 mm radius	< 0.197 in. radius
150°F (66°C), 90 days, 3.0V	G 42	< 10 mm radius	< 0.4 in. radius
Non-shielding properties (Does not shield cathodic protection currents)	Internal <b>Polyguard</b>	Pass (non-shielding)	Pass (non-shielding)
Dielectric Strength (breakdown voltage, KV)	D 149	> 12 KV (9.45 V/μm)	> 12 KV (240 V/mil)
Adhesion to primed surface	D 1000 Method A	35 N/10mm width	20 lbs. F/in. width
Adhesion to polyethylene	D 1000 Method A	28 N/10mm width	16 lbs. F/in. width
Impact Resistance	G 14	2.6 g/cm	23.0 in./lb.

## contact us



6714 Bourgeois Rd.  
Houston, TX 77066

Phone : 281-580-5700

Email: [pipeline@polyguard.com](mailto:pipeline@polyguard.com)

Web : [www.polyguard.com](http://www.polyguard.com)

Social : [@polyguardproducts](https://www.instagram.com/polyguardproducts)

