


Deckguard® HT

PRODUCT OVERVIEW



Deckguard® HT is designed to help in high temperature applications. The high temperature resistance allows the membrane to be exposed to heat of 260° or less. It has superior adhesion to the roof deck. It is self-sealing and will seal around nails which will resist leakage caused by water backing up due to ice dams or wind driven rains.

- · High heat membrane, can be exposed to heat up to 260°F for 60 days
- · Film release for ease of application.
- · Anti-Skid backer
- · Self-sealing: will seal around nails to resist leakage created by water backing up due to ice dams or wind driven rains.
- · Waterproofs potential leak areas such as protrusions, skylights, valleys, and other flashing areas.

Property	Test Method	Typical Value
Film Color		Blue/White
Total Underlayment Thickness		40 mils
Softening Point	ASTM D 36	260°F
Elongation - Ultimate failure of Rubberized asphalt	ASTM D 412 Modified Die C	> 184%
Tensile Strength	ASTM D 412 Modified Die C	338 PSI
Puncture Resistance	ASTM E 154	> 22 lb _f
Low Temperature Pliability	ASTM D 146	No effect
Permeance	ASTM E 96	0.01
Nail Sealability	ASTM D 1970	PASS
Thermal Stability	ASTM D 1970	PASS
Peel Adhesion	ASTM D 1970	> 15 lb./in. width
Lap Adhesion	ASTM D 1970	> 10 lb./in. width

REV062824















COMPANION PRODUCTS















